

# RODIM Wheel Protection Masking

Published: 09.08.2017

Latest update: 15.09.2017

## MASKING



### Storage Remarks

Storage time is 12 months from delivery date. Keep storage temperature between + 20° C / ± 10° C and the relative humidity by 30 – 90%.

Storage in closed rooms. Avoid exposure of UV-radiation.

### Available in:

Article number	Article description
45129155	RODIM Wheel Protection Masking System

### Compatible with:

Article number	Article description
45130436	RODIM Dispenser for Masking Film

### Packaging:

1 Piece – 80 Units	1300 x 1300mm
--------------------	---------------

### Properties:

Property	Value & measuring unit	Measuring Method
Density	0,933 g /cm <sup>3</sup>	DIN EN 1183
Thickness	40 µm	GPA (Thickness Profile)
Tensile Strength machine direction	35 N / mm <sup>2</sup>	ASTM D 882
Tensile Strength transverse direction	25 N / mm <sup>2</sup>	ASTM D 882
Elongation at break machine direction	670 %	ASTM D 882
Elongation at break transverse direction	1000 %	ASTM D 882

# RODIM Wheel Protection Masking

## MASKING

Property	Value & measuring unit	Measuring Method
Dart drop	4,5 g / $\mu\text{m}$	ASTM 1709-91
Dimension and Design	1300 x 1300	
Coefficient of friction inner side	~ 0,26	DIN EN ISO 8295
Coefficient of friction out side	~ 0,19	DIN EN ISO 8295
Surface Resistance	2 x 10 <sup>11</sup> $\Omega$	DIN IEC 93

This technical information has been given to the best of our knowledge. The above-mentioned standards are average values and no granted assurance of special properties. This statement is limited to the material, in the state as it leaves the manufacturer and does not include possible modifications by conversion and/or handling after dispatch.