

RODIM Comfort Masking Film

Published: 01.06.2019

Latest update: 01.06.2019

MASKING



Storage Remarks

Storage time is 12 months from delivery date. Keep storage temperature between + 20° C / ± 10° C and the relative humidity by 30 – 90%. Storage in closed rooms. Avoid exposure of UV-radiation.

Available in:

Article number	Article description
45220953	RODIM Comfort Masking Film 5m x 120m

Compatible with:

Article number	Article description
45130436	RODIM Dispenser for Masking Film

Packing:

1 Piece per box

Properties:

Property	Value & measuring unit	Measuring Method
Density	Ca. 1,143 g /cm ³	DIN EN 1183
Thickness	14 µm	GPA (Thickness Profile)

RODIM Comfort Masking Film

MASKING

Property	Value & measuring unit	Measuring Method
Tensile Strength machine direction	38,3 N / mm ²	ASTM D 882
Tensile Strength transverse direction	24,9 N / mm ²	ASTM D 882
Elongation at break machine direction	210 %	ASTM D 882
Elongation at break transverse direction	390 %	ASTM D 882
Dart drop	4,3 g / μm	ASTM 1709-91

This technical information has been given to the best of our knowledge. The above-mentioned standards are average values and no granted assurance of special properties. This statement is limited to the material, in the state as it leaves the manufacturer and does not include possible modifications by conversion and/or handling after dispatch.