

RODIM Glass Fibre Putty

RODIM Glass Fibre Putty

Application:

RODIM Glass Fibre Putty can be used for filling deep surface irregularities and dents on bodies of cars, commercial vehicles, buses, and railway vehicles.

Key Features:

- Good sandability
- Smooth and even filling
- High build
- Adhesion on metal substrates
- For repairing small rust spots.

Remarks:

- For steel substrates only.
- Not suitable for zinc, galvanized steel, plastic and aluminum substrates.
- The substrate must be clean, dry and free from grease.
- Stir well before use.
- Paste-like at 20°C
- Color: green

Density

1.78 g/cm³

Handling



Minimum reaction temperature +10°C.

Potlife: 3 - 4 min at 20°C

Shelf life 12 months at 18 - 20°C in a sealed original container.

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/II(b)(250)<250: The EU limit value for this product (product category: IIB.b) in ready-for-use form is max 250 g/litre of VOC. The VOC content of this product is < 250g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

RODIM Glass Fibre Putty

RODIM Glass Fibre Putty

**Mixing Ratio**

100 % by weight

RODIM Glass Fibre Putty

**Hardener**

2-3 % by weight

RODIM BPO Hardener Hardener paste for body filler

Do not add too much hardener paste as this might cause bleeding and a change of color in the finish.

Drying**Drying at 20°C**

15-20 min

**Orbital sanding, dry**Dry sand with P80 - P120
Then dry sand with P120 - P240.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/II(b)(250)<250: The EU limit value for this product (product category: IIB.b) in ready-for-use form is max 250 g/litre of VOC. The VOC content of this product is < 250g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.