

RODIM Masking Film

Published: 09.08.2017

Latest update: 09.08.2017

MASKING



Storage Remarks

Storage time is 12 months from delivery date. Keep storage temperature between + 20° C / ± 10° C and the relative humidity by 30 – 90%. Storage in closed rooms. Avoid exposure of UV-radiation.

Available in:

Article number	Article description
45128992	RODIM Masking Film 6m x 150m 11µm

Compatible with:

Article number	Article description
45130436	RODIM Dispenser for Masking Film

Packaging:

1 Piece	6m x 150m 11µm
---------	----------------

Properties:

Property	Value & measuring unit	Measuring Method
Density	0,95 g /cm ³	DIN EN 1183
Thickness	11 µm	GPA (Thickness Profile)
Tensile Strength machine direction	70 N / mm ²	ASTM D 882
Tensile Strength transverse direction	28 N / mm ²	ASTM D 882

RODIM Masking Film

MASKING

Property	Value & measuring unit	Measuring Method
Elongation at break machine direction	422 %	ASTM D 882
Elongation at break transverse direction	893 %	ASTM D 882
Dart drop	3,45 g / μm	ASTM 1709-91
Dimension and Design	6m x 150m	

This technical information has been given to the best of our knowledge. The above-mentioned standards are average values and no granted assurance of special properties. This statement is limited to the material, in the state as it leaves the manufacturer and does not include possible modifications by conversion and/or handling after dispatch.